

PRODUCT SPECIFICATION

2200-G

UV Adhesive

Description:

Formulated for structural bonding applications, this single-component, high viscosity UV curable adhesive cures in seconds upon exposure to ultraviolet light. It creates a flexible, impact-resistant bond across glass, metal, and various other substrates.

Engineered for long-term durability, the adhesive exhibits exceptional resistance to prolonged humidity, water exposure, and environmental weathering. Its high viscosity provides controlled placement on vertical surfaces and larger gap filling, making it ideal for general-purpose structural bonding where superior strength and environmental stability are required.

Typical Properties of Cured/Uncured Material:

Liquid State		Cured State	
Base	Urethane Methacrylate	Tensile Strength, ASTM D882 (psi)	3550
Colour	Clear, amber	Elongation @ break (%)	15
Specific Gravity (25°C)	1.1	Hardness, ASTM D2240 Shore D	65
Refraction Index (25°C)	1.495	Tg, ASTM D3418-82 (°C)	45
Viscosity (cP)	2000 - 2500	Water Absorption, ASTM D570 (%)	5.8

UV Curing System:

Lamp Type	5" x 5" Flood	3/16" Spot	1" x 6" Focused
Max. Lamp Intensity @ 365 nm	300 mW/cm ²	4000 mW/cm ²	8000 mW/cm ²
Adhesive Absorption Range (nm)	300 - 500	300 - 500	300 - 500
Cure Speed (Sec)			
Glass to Glass Bonding	14	12	<4
Surface Cure Speed	18	18	<4

Bond Strength

(Shear Strength, psi, ASTM D4501):

Substrate	psi	N/mm ²
Steel to Glass	3550	24
Aluminum to Glass	3250	22
Glass to Glass	4000	27

Cure Conditions:

Cure can be achieved using both low and high-intensity UV light sources. Under a low UV intensity of 30 mW/cm, highly transmissive substrates with joint gaps under 0.25 mm (0.010") cure in 5 seconds, while gaps of 1.75 mm to 2.25 mm (0.070" to 0.090") cure within 10 to 20 seconds. Under a high UV intensity of 100 mW/cm, highly transmissive substrates with gaps under 0.25 mm (0.010") cure in 2 seconds, while larger gaps of 2.5 mm to 5.0 mm (0.100" to 0.200") achieve full cure within 10 to 20 seconds.

Directions For Use:

This adhesive is UV sensitive. Exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling. Adhesive product should be dispensed from applicators with black feed lines. For best performance bond surfaces should be clean and free from grease.

UV cure rate is depends on lamp intensity, distance from light source, depth of cure needed or bond line gap and light transmittance of the substrate through which the radiation must pass.

Recommended intensity for cure in an adhesive application are 40-mW/cm² minimums with an exposure time of 5-6 times the fixture time at this same intensity. For tack free surface cure, as necessary in coating, potting or tacking applications, higher intensity UV is required.

Disclaimer:

The data contained herein are furnished for informational purposes only and are believed to be reliable. However, The company does not assume responsibility for any results obtained by persons over whose methods The company has no control. It is the user's responsibility to determine the suitability of The company products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any The company products. The company specifically disclaims all warranties express or implied, including warranties of saleability and suitability for a particular purpose arising from sale or use of The company products. The company further disclaims any liability for consequential or incremental damages of any kind including lost profits.